## Face Material

Gloss white  cavitated polypropylene

| | | |
|---|---|---|
| Type | BOPP film | |
| Colour and Finish | Pearlized | |
| Weight | 53  gsm ± 3% | ISO 536 |
| Thickness | 70 µ ± 4% | ISO 534 |

## Adhesive

General purpose   Acrylic permanent featuring high clarity and cohesion with strong adhesion to apolar substrates (like PE and PP)

| | | |
|---|---|---|
| Type | Acrylic based | |
| Min. Appl.Temp | 0˚c | |
| Service TEMP | -20/+80 ˚c | |
| Initial Tack | 8 N/25mm | FINAT FTM 9 |
| Shear | High | FINAT FTM18 |
| Final Adhesion | 8 N/25mm | FINAT  FTM 2 |

## Liner

| | | |
|---|---|---|
| Type | One side siliconized Glassine | |
| Colour and Finish | White | |
| Weight | 60 gsm ±5% | ISO 536 |
| Thickness | 55 µ ± 5% | ISO 534 |
| Transparency | >50% | DIN 53 147-46 |

## Application

Specially designed for logistics and  promotional labels in consumer product

## Printing Methods

Printable with letterpress, flexo , offset  and gravure.

Testing for suitability between media , printers and inks is always recommended prior to use.

## Shelf life

Two years under storage conditions (This material must be stored at a temperature of 23±2 ˚c and 50±5 ˚c of relative Humidity.)
Keep the material in the original packaging when not used in order to protect it from dust and contamination

Do not expose to direct sunlight or heat sources.